

description

Uncoated papers and boards made with E.C.F. pulp, certify FSC. Felt marked on both sides. Special "Stucco" treatment on both sides, allow a particularly bright and sharp printing. Available in "Gesso" colour.

range

size grain substance

72x101 LG 120 160 240 300

technical features
ref. standard/instrument
unit of measure

substance	VSA	Taber stiffness 15° ISO 2493		tensile strength ISO 1924	
ISO 536	ISO 534				
g/m²	cm³/g	mΝ		kN/m	
		long±10%	cross±10%	long±10%	cross±10%
120 ± 3%	1,3	16	8	8,5	3,9
160 ± 3%	1,3	30	12	9,1	4,5
240 ± 5%	1,3	140	50	14,4	6,5
300 ± 5%	1,3	280	100	18,3	9,1

Brightness - ISO 2470 (R457) - 94% \pm 2 Relative Humidity 50% \pm 5 ref. TAPPI 502-98

ecological features



CHLORINE FREE GUARANTEED







The product is completely biodegradable and recyclable. Special runs available upon request.

 $The Company \ reserves \ the \ right to \ modify \ the \ technological \ features \ of \ the \ product \ in \ relation \ to \ market \ requirements.$



Stucco Acquerello papers and boards are ideal for any kind of publishing, packaging and commercial printing. They are held in high regard fo de luxe publications, brochures and and commercial printings - wherever the need is to exploit the features of a marked paper with the merits and the printing performance of coated paper.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The characteristic felt marking requires specific printing pressure settings.

printing suggestions

Good results in varnishing and plastic laminating. The surface roughness typical of marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

converting suggestions

